

OLIMAG SAND inc.  
 2899 BLVD. Frontenac East  
 Thetford Mines (Quebec) Canada G6G 6P6  
 Tel. : (418) 338-3562  
 E-MAIL: [info@olimag.com](mailto:info@olimag.com)

**OLIMAG** Inc.  
**Sands**  
[www.olimag.com](http://www.olimag.com)

# JETMAG®

## SYNTHETIC OLIVINE PYROXENE SAND FOR BLAST CLEANING

### ADVANTAGES:

- Excellent sanding quality with a highly competitive cost / performance, fast execution and reduced sand consumption.
- Its chemical and mineralogical composition makes JETMAG® a non-toxic, non-hazardous product for an improved workplace quality for users
- Has less than 1% of free silica.
- Produce a safe and limited dust work environment, great productivity in enclosed spaces
- Reduce cost of waste management due to its lighter weight
- Can be recycled 3 to 4 times with adequate recycling system in place

### OUR STANDARD GRANULOMETRY

JETMAG	DEPTH OF CAVITIES IN 1/1000 OF AN INCH	MAIN USAGES
16-60	4 to 6	Hard rust, painted and rusted steel, premetallization, deep cavities, boat and bridges surfacing, concrete
30-60	2.5 to 4	Acier peint ou rouillé de structure, équipements industriels, machinerie lourde, camions
32B4	2 to 3	New and painted steel, light rust, trucks, wheels
35-70	1.5 to 2.5	Automotive (car body shop), light cavities, new steel, stainless steel
60-B2	0.5 to 1	Stainless steel, fiberglass, aluminum, wood

Chemical analysis		Physical properties
ELEMENTS	% weight	
MgO	38 to 42	Specific gravity : 2.8 – 2.9 g/cc*
SiO <sub>2</sub> *	39 to 47	Density : 78 à 82 lbs/pi <sup>3</sup> * (1.25 to 1.31 g/cm <sup>3</sup> )
Fe <sub>2</sub> O <sub>3</sub>	7 to 10	Angular shape particles
AL <sub>2</sub> O <sub>3</sub>	0.3 to .13	Water absorption: absorb no humidity
CaO	0.8 to 1	Hardness : 7 À 7,5 on the Mohs scale
Others	1 to 2	* Upon granulometry

\* More than 99 % of the silica is chemically link to magnesium with less than 1 % de free silica.

Revision : January 2022	Technical data JETMAG EN	By : Ben Piuze	Public/Fiche Technique
-------------------------	--------------------------	----------------	------------------------